

Data Sheet

1640 CR(Neoprene)/SBR Blend 40 Shore Rubber Sheeting

Data Sheet Type	Final
Material Reference	1640
Polymer	SBR/CR BLEND
Date Issued	02/06/26



Description

A 40° Shore Neoprene (CR)/SBR Blended Rubber Sheeting for General Purpose or Gasketing use. A Hybrid Material that will carry some performance characteristics of Neoprene and some of SBR and is suitable for a variety of Lower Technology Sealing Applications. Choose this softer material for use with distorted or uneven surfaces.

Specifications	Values	Test Methods
Available from Stock	Yes	None
Colour	Black	None
Compression Set(22 Hours @ 70°C)	35 % Maximum	ASTM D395 Method B
Elongation at Break	300 % Minimum	ASTM D412
Highest Recommended Working Temperature	90 °C Maximum	None
Intermittent Working Temperature	100 °C Short Bursts Only	None
Lowest Recommended Working Temperature	-25 °C Minimum	None
Shore Hardness (Shore A)	40 ° Shore +/-5°	ASTM D2240
Specific Gravity	1.4 g/cm 3 +/-0.05	ASTM D2240
Standard Roll/Sheet Size	1400mm x 10 Metres Range	None
Tensile Strength	3.5 MPA Minimum	ASTM D412

**Important Notes about this Material Data Sheet**

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.