

Data Sheet

Nitrile Bonded Cork High Temperature

| | |
|--------------------|--|
| Data Sheet Type | Final |
| Material Reference | Nitrile Bonded Cork High Temperature |
| Polymer | NBR |
| Date Issued | 02/06/26 |



Description

An excellent general purpose gasketing material, suitable for high temperature applications with good wear resistance and compressibility characteristics, making it ideal for a automotive and industrial gasketing applications.

| Specifications | Values | Test Methods |
|---|-------------|--------------|
| Colour | Black | None |
| Compressibility | 40 % | ASTM F104 |
| Compression Set | 20 % | ASTM F104 |
| Density | 650 Kg/m3 | ASTM F104 |
| Flexibility | No Cracks | ASTM F104 |
| Highest Recommended Working Temperature | +130 °C | None |
| Lowest Recommended Working Temperature | -20 °C | None |
| Oil Swell ASTM 1 | -5 / +10 % | ASTM F104 |
| Oil Swell IRM903 | +10 / +40 % | ASTM F104 |
| Recovery | > 80 % | ASTM F104 |
| Shore Hardness (Shore A) | 62 ° Shore | None |
| Tensile Strength | 10 kg/cm | ASTM F104 |

Purposes



Water Resistant



Wear Resistant

Important Notes about this Material Data Sheet

This datasheet has been carefully compiled to advise you, our customer, in the best possible way. The information, figures, test values, and data correspond to actual engineering standards and are the result of many years of tests and trials. As individual operating conditions influence the application of each product, the information supplied in this datasheet can only be seen as a rough guideline. In every case it is the sole responsibility of the customer to evaluate his individual requirements, in particular whether the specified properties of our products are sufficient for the intended use. This datasheet is subject to alteration without prior notice. All mentioned values contained herein are guiding values representing long-term experience averages. Please be aware that Test Results for individual Material Batches will only be provided if requested at the time of order and may be subject to additional charges and/or lead times. This Data Sheet supersedes all previous data sheets and any other data previously provided either Verbally, Electronic or Written, with reference to the above Material Grade.